

ELEGOO ABS-Like Resin

Max. force (KGF) 167.1±10%

Tensile strength (MPa) 39.39±10%

Deformation at the point of maximum force (mm) 6.41±10%

Yield point elongation (%) 6.49±10%

Elongation at break (%) 14±10%

Flexural strength (MPa) 40.54±10%

Flexural modulus (MPa) 1089.62±10%

Impact strength (j/m) 205±10%

Tensile modulus(MPa) 538.9±10%